

UDC 621.9

Gyula Varga, Viktoria Ferencsik  
University of Miskolc, Institute of Manufacturing Science

## **EXAMINATION OF RESIDUAL STRESSES ON DIAMOND BURNISHED CYLINDRICAL SURFACES**

### **ABSTRACT**

*Cold plastic finish manufacturing methods such as surface rolling, burnishing and surface hardening with shot peening play important role in the lifetime increasing manufacturing as compressive residual stress remains in near surface layers of the workpiece. This paper deals with examination of changing of residual stress caused by burnishing using diamond tipped tools. The diamond burnishing executed on outer cylindrical surfaces is a finishing manufacturing operation which results high accuracy and fine surface texture. The aim of the examinations was to determine how the burnishing speed, feed rate and burnishing force has affect on the residual stresses in case of diamond burnishing of low alloyed aluminium shafts. The Taguchi type Factorial experiment design was used for planning of experiments. The measurement of residual stresses was performed by an X-ray diffraction method. The evaluation of measured results was done by a specially specified ratio to determine the parameter set which results the best residual stress values in between the given range of technological parameters.*

### **1. INTRODUCTION**

Nowadays, the researches regarding shape correctness [1] and surface roughness of the manufactured surfaces [2 - 4] are accelerated. More and more researches deal with residual stresses [5] and the examination of changing of texture on the surface of the workpiece [6]. This is in connection with the tasks determined in Industry 4.0 as well in which the development of production engineering and manufacturing processes is an important task. These tasks can be done in environmentally conscious way too [8 - 9]. These are in tight connection with the lifetime and reliability [10] of the produced parts. The accuracy of differently manufactured parts were analysed, examined, and compared [11] because parts can be produced with higher and higher accuracy by the newly developed cutting tools [12 - 14]. Life time of products can be increased in profoundly great extent by assembling these parts into the engineering products.

In industrial practice, the quality requirements involve the knowledge of the value and distribution of residual stresses in the near surface layer particularly parts of motor vehicle exposed to fatigue. There are several possibilities for direct creation of compressive stress for preventing of the development and spread of fatigue cracking such as cementing, blasting, calendaring and roll burnishing [15]. Burnishing of surfaces belongs to here as well, which can be more effective, more efficient than conventional fine surface machining procedures (e.g. grinding,

lapping, polishing). Burnishing can make manufacturing process more cost effective.

The Taguchi type factorial experimental design was used in this research [16 - 17] which is valid in between the minimum and maximum values of the input parameters. The classification and short description of design of experiment methods was prepared by Drégelyi-Kiss et. al. [18].

In the present experiments input parameters were: burnishing speed ( $v_b$ ), feed ( $f$ ), and burnishing force ( $F_b$ ) while the output parameters are: tangential ( $\sigma_t$ ) and axial ( $\sigma_a$ ) residual stress.

## 2. BURNISHING OF OUTER CYLINDRICAL SURFACES

During burnishing, because of the kinematic interaction of work piece and burnishing tool, the near surface layer of the work piece is deformed [19]. Kinematic relations are demonstrated in Fig. 1 [20].




Figure 1 – Kinematics of burnishing [20]

There are several advantages of this procedure applying sliding relative movement: - surface roughness can be reduced effectively, - the micro hardness of near surface layer can be increased by reordering of dislocations, - corrosion resistant ability can be improved, - shape correctness of the cylindrical surfaces can be improved, - does not require huge amount of coolant and lubricant application, so means low environment load [21].

In case of outer cylindrical surfaces diamond burnishing is applied as a final finishing procedure resulting high accuracy, low surface roughness. The diamond burnishing can be realized on conventional lathes and CNC lathes as well. The applied tool tip can be hardened steel, carbide, ceramics, or natural or artificial diamond.

The reduction of surface roughness and the other advantages mentioned above occur because of static contact being in between of burnishing tool and surface of work piece, typically in the depth of  $0,01 \div 0,2$  mm [22 - 25]. During the

manufacturing process, the tensile residual stress being in the surface zone after machining is converted into compressive residual stress which is the cause that fatigue behaviour is improving of the part under dynamic load.

### **3. EXPERIMENTAL CONDITIONS**

#### **3.1. Features of the workpiece to be burnished**

The material and the hardness of the workpiece to be burnished can be differed for a very wide range. For the experiments, we have chosen lightly alloyed aluminium material because it's employment is supported for choice by industries [26 - 29], due to its low density and good mechanical properties.

The examination of the chemical composition of the lightly alloyed aluminium was executed on a scanning electron microscope type Apollo X. Measuring was done on 3 points and the averaged results are shown in Table 1.

Table 1 – Chemical composition of the aluminium alloy

Elements	Al	Si	Fe	Cu	Bi	Pb
Averaged wt% (weight percent)	92.11	0.19	0.84	5.65	0.46	0.74

#### **3.2. Burnishing parameters**

During the experiments, a CNC lathe with flatbed by firm OPTIMUM type OPTIturn S600 was used which is located in the workshop of Institute of Manufacturing Science at University of Miskolc. The tool tip was PCD (polycrystalline diamond) with 3.5 mm radius and the kinematic viscosity of the applied oil was 70 mm<sup>2</sup>/s. Fig. 2 shows the process in progress.

The matrix of the Taguchi type Full Factorial Experimental Design can be seen on Table 2, which contains the burnishing parameters in natural dimensions and their transformed values.




Figure 2 – Burnishing process on OPTIMUM OPTIturn CNC machine

Table 2 – Applied burnishing parameters

Sign of specimen	Parameters of burnishing			Transformed parameters		
	$v_b$ [m/min]	$f$ [mm/rev]	$F_b$ [N]	$X_1$	$X_2$	$X_3$
1	15	0.001	10	-1	-1	-1
2	30	0.001	10	+1	-1	-1
3	15	0.005	10	-1	+1	-1
4	30	0.005	10	+1	+1	-1
5	15	0.001	20	-1	-1	+1
6	30	0.001	20	+1	-1	+1
7	15	0.005	20	-1	+1	+1
8	30	0.005	20	+1	+1	+1

### 3.3. Measuring of the residual stress

Residual stress is a process-induced stress, frozen in a molded part, that exists in a body in the absence of external loading or thermal gradients. In a structural material or component, residual stresses exist in the object without the application of services or other external loads. They affect a part similarly to externally applied stresses.

Important residual stress measurements are made by the following methods: hole-drilling method, magnetic field, ultrasonic testing and X-ray diffraction method [30].

In materials because of the macroscopic residual stress the atomic cores in the lattice points are put of their balance [31]. In the point of view of crystallography, it means that the parameters of the lattice are changing. Distance between lattice planes are changed because of the residual stress, these distances can be measured, so the values of the stress can be calculated from them.

Incidentally residual stress can be hardly established in lower rigid materials. It causes smaller changing in material properties as it can be more relaxed [22].

During measuring process, the wave-length of the X-ray is known and the dislocation of the Bragg-angle is measured that is caused by the changing of lattice planar distances. The formula (1) was applied what is called Bragg-equation [32]:

$$n\lambda = 2d_{hkl} \sin \Theta, \quad (1)$$

where:  $n$ : integer determined by order given

$\lambda$ : wave-length of X-ray

$d_{hkl}$ : spacing between the planes in the atomic lattice

$\Theta$ : angle between the incident ray and the scattering planes

Fig. 3 [33] illustrates crystal co-ordinate system with the applied marks and calculating methods.





Figure 3 – Demonstration of crystal systems [33]

Fig. 4 illustrates the basic principles of the described method with its adaptation into practice which was executed on an X-ray diffraction measuring machine type Stresstech Xstress 3000 G3R. One of the main advantage of using this measuring machine is that it can realize non-destruction test.

a)



b)



Figure 4 – Diffraction of X-ray method  
a) theoretic background by a crystal lattice [32], b) and realization

The diffraction of X-rays, of course, was not only between 2 nearby atomic planar, they are reflecting forward. The X-rays landed from this further planer have to meet in the same phase and the criterion of it is that the difference of device between reflected waves being equal to integral multiples of wave-length, so in formula (1)  $n = 1, 2, 3, \dots$  must be substituted [32].

Measuring was done on 4 points at  $45^\circ$  in tangential and axial direction too because it was supposed that the direction of the processing has influence on the changing of the stress condition. Fig. 5 shows the main stress directions [34].




Figure 5 – The main stress direction of cylindrical workpiece [34]

#### 4. RESULTS AND EVALUATIONS

For evaluation of measured data an improvement ratio was introduced, which is shown in formula (2):

$$\rho_\sigma = \frac{|\sigma_b - \sigma_t|}{|\sigma_b|} \cdot 100, \% \quad (2)$$

where:  $\rho_\sigma$  Improvement ratio of residual stresses ( $\sigma$ ). This is a dimensionless ratio, which textures the changing of residual stress occurring because of manufacturing,

- $\sigma_t$  Residual stress remains after turning,
- $\sigma_b$  Residual stress remains after burnishing.

The higher the value of  $\rho_\sigma$ , the greater the improvement due to burnishing. Measured data and the improvement ratios of residual stresses, calculated by formula (1), in tangential and axial directions are summarized in Table 3.

Table 3 – Measured residual stress values and the calculated improvement ratios

Sign of specimen	$\sigma_t$ [MPa]		$\rho_{\sigma t}$ [%]	$\sigma_a$ [MPa]		$\rho_{\sigma a}$ [%]
	after turning	after burnishing		after turning	after burnishing	
1	23.470	- 97.230	124.14	- 6.075	- 163.300	96.27
2	23.470	- 148.350	115.82	- 6.075	- 191.625	93.83
3	23.470	- 209.325	111.21	- 6.075	- 220.500	97.24
4	49.250	- 200.352	124.58	10.475	- 294.975	103.55
5	23.470	- 89.600	126.19	- 6.075	- 105.875	94.26
6	49.250	- 71.800	168.59	10.475	- 82.575	112.69
7	23.470	- 131.475	117.85	- 6.075	- 207.950	97.08
8	49.250	- 150.075	132.82	10.475	- 241.125	104.34

Application of Factorial Experiment Design method empirical formulas (3) and (4) were created from the calculated values. Calculations and axonometric figures (Fig. 6-7) were prepared using „MathCAD 16.0” software.




Figure 6 – Changing of improvement ratio of the residual stresses measured in tangential direction

$$\rho_{\sigma_t} = 203.2125 - 5.116 \cdot v_b - 2.208 \cdot 10^4 \cdot f - 6.21 \cdot F_b + 1.18 \cdot 10^3 \cdot v_b \cdot f + 0.42 \cdot v_b \cdot F_b + 0.43 \cdot f \cdot F_b - 81.867 \cdot v_b \cdot f \cdot F_b \quad (3)$$




Figure 7 – Changing of improvement ratio of the residual stresses measured in axial direction

$$\rho_{\sigma_a} = 128.8275 - 2.027 \cdot v_b - 7.357 \cdot 10^3 \cdot f - 2.825 \cdot F_b + 476.833 \cdot v_b \cdot f + 0.172 \cdot v_b \cdot F_b + 542.75 \cdot f \cdot F_b - 33.15 \cdot v_b \cdot f \cdot F_b \quad (4)$$

## 5. SUMMARY

Following statements can be done on the base of executed and evaluated experiments:

In tangential direction, perpendicular to the direction of manufacturing, the value of the improvement ratio of residual stresses was the highest,  $\rho_{\sigma_t} = 168,59 \%$ , when the burnishing parameters were:  $v_{b2} = 30$  m/min;  $f_1 = 0.001$  mm/rev; and  $F_{b2} = 20$  N. Using these burnishing parameters, in axial direction the maximum value of the improvement ratio of residual stresses is  $\rho_{\sigma_a} = 112,69\%$ .

Examining the evaluated results can be stated that the effect of burnishing speed is the most dominant when the burnishing force is higher ( $F_{b2} = 20$  N) and the feed rate is smaller ( $f_1 = 0.001$  mm/rev). The burnishing speed and burnishing force show strong interaction. It requires further investigation for what extent can these burnishing parameters increased further.

## ACKNOWLEDGEMENTS

“The described study was carried out as part of the EFOP-3.6.1-16-00011 “Younger and Renewing University – Innovative Knowledge City – institutional development of the University of Miskolc aiming at intelligent specialisation” project implemented in the framework of the Szechenyi 2020 program. The realization of this project is supported by the European Union, co-financed by the European Social Fund.”

The authors greatly appreciate the support of the National Research, Development and Innovation Office – NKFIH (No. of Agreement: NKFI-125117).

**References** 1 M.H. El-Axir, O.M. Othman, A.M. Abodiena: **Improvements in Out-of-roundness and Microhardness of Inner Surfaces by Internal Ball Burnishing Process**, J Mat Proc. Tech. 196 Iss. 1-3, (2008) 120–128. 2 J. Kundrak, K. Gyani, V. Bana: **Roughness of ground and hard-turned surfaces on the basis of 3D parameters**. Int. J. of Advanced Manuf. Techn., 38 (1-2) (2008) 110-119. 3 C. Felho, J. Kundrak: **Characterization of topography of cut surface based on theoretical roughness indexes**, Key Eng. Mater. 496 (2012) 194-199. 4 G. Varga: **Effects of Technological Parameters on the Surface Texture of Burnished Surfaces**, Key Engineering Materials, Precision Machining VII, 581 (2014) 403-408, ISSN 1013-9826. 5 M. Novák: **Surfaces with High Precision of Roughness after Grinding**. Manufacturing Technology, 12 (2012) 66-70. 6 J. Kundrák, Z. Gácsi, K. Gyáni, V. Bana, G. Tomolya: **X-ray diffraction investigation of white layer development in hard-turned surfaces**. Int. J. of Adv. Manuf. Techn., 62 (5-8), (2012) 457-469. 7 P. Tamás, B. Illés: **Process improvement trends for manufacturing systems in INDUSTRY 4.0**, Academic Journal of Manufacturing Engineering 14:(4) pp. 119-125. (2016). 8 P. Tamás, B. Illés, P. Dobos: **Waste reduction possibilities for manufacturing systems in the industry 4.0**, IOP Conference Series: Materials Science and Engineering 161: pp. 1-8. (2016). 9 M. Rusko, R. Kralikova: **Implementation of environmental oriented monitoring in the manufacturing company**. Advanced Materials Research, vols. 816-817 (2013) 1225-1230. 10 W. Zebala, B. Slodki, G. Struzikiewicz: **Productivity and Reliability Improvement in Turning INCONEL 718 Alloy - Case Study**. Eksploatacja i Niezawodnosc - Maintenance and Reliability, 15, Iss. 4 (2013) 421-426. 11 J. Kundrák, A.G. Mamalis, A. Markopoulos: **Finishing of hardened boreholes: Grinding or hard cutting?** Materials and Manufacturing Processes, 19 (6) (2004) 979-993. 12 I. Sztankovics, J. Kundrák: **Effect of the Inclination Angle on the Defining Parameters of Chip Removal in Rotational Turning**, Manufacturing Technology, ISSN 1213–2489 (2014) 97-104. 13 J. Beňo, I. Maňková, M. Vrabel', D. Kottfer: **Roughness Measurement Methodology for Selection of Tool Inserts**, Measurement, Vol. 46, Iss. 1, January (2013), 582–592- ISSN 0263-2241. 14 G. Dezső, J. Herman, F. Szigeti: **Two-dimensional physical modelling of the cutting wedge**. Int. J. of Engineering, X. 1. (2012) 155-158 ISSN 1584-2665. 15 V. Mertinger, J. Sólyom, M. Benke: **Application of MonoCap optics in X-ray diffraction examinations**, Anyagvizsgálók Lapja, 2012/1, pp.: 60-64, ISSN: 1787-507 (In Hungarian). 16 G. Taguchi: **System of experiment design, 1. Experimental design**, UNIPUB, Kraus International Publications, White Plains, New York, (1987) ISBN 0-527-91621-8. 17 L. Fridrik: **Chosen chapters from the topics of experimental design of production engineering**, Műszaki Könyvkiadó, Budapest, 1987 (In Hungarian). 18 Á. Drégelyi-Kiss, R. Horváth, B. Mikó: **Design of experiments (DoE) in investigation of cutting technologies**, Development in Machining Technology, Vol. 3. Ed.: W. Zebala, I. Manková, Cracow University of Technology (2013) 20-34. 19 L. Janczewski, D. Tobała, W. Brostow, K. Czechowski, H. Lobland, M. Kot, K. Zagórski: **Effects of ball burnishing on surface properties of low density polyethylene**. Tribology International 93 (2016), pp.: 36-42. 20 D. Tobała, P. Rusek, K. Czechowski, T. Miller, K. Duda: **New Indicators of Burnished Surface Evaluation – Reasons of Application**, Metrol. Meas. Syst., Vol. XXII (2015), No. 2, pp. 263–274. 21 G. Varga: **Can Diamond Burnishing be Done in an Environmentally Friendly Way?** Applied Mechanics and Materials, Vol.

474 (2014), pp.: 411-416. **22** L. Luca, S. Neagu-Ventzel, I. Marinescu: **Effects of working parameters on surface finishing ball-burnishing** of hardened steels. Precision Engineering (Elsevier) 29 (2005) pp.: 253-256 DOI:10.1016/j.precisioneng.2004.02.002. **23** T.A. El-Taweel, M.H. El-Axir: **Analysis and optimization of the ball burnishing process through the Taguchi technique**, The International Journal of Advanced Manufacturing Technology (2009) 41: pp. 301-310, DOI 10.1007/s00170-008-1485-6. **24** G. Varga: **Effects of Technological Parameters on the Surface Texture of Burnished Surfaces**, Key Engineering Materials, Volume 581: (2014) Precision Machining VII, pp.: 403-408, 2014, ISSN 1013-9826, DOI:10.4028/www.scientific.net/KEM.581.403. **25** Q.-N. Banh, F.-J. Shiou: **Determination of optimal small ball-burnishing parameters for both surface roughness and superficial hardness improvement of STAVAX**, Arab J Sci Eng. (2016)41, DOI 10.1007/s13369-015-1710-1, pp.:639-652. **26** A. Akkurt: **Comparison of roller burnishing and other methods of finishing treatment of the surface of openings in parts from tool steel D3 for cold forming**, Metal Science and Heat Treatment, Vol. 53, Nos. 3 – 4, July, 2011 (Russian Original Nos. 3 – 4, March – April, 2011), pp.: 145-150. **27** M.R. Stalin John, P. Suresh, D. Raguraman, B.K. Vinayagam: **Surface characteristics of low plasticity burnishing for different materials using lathe**. Arab J SciEng. (2014) 39, pp.: 3209–3216. **28** G.H. Majzoobi, F. Zare Jouneghani, E. Khademi: **Experimental and numerical studies on the effect of deep rolling on bending fretting fatigue resistance of AL7075**, The International Journal of Advanced Manufacturing Technology (2015): pp. 301-310, DOI 10.1007/s00170-015-7542-Z. **29** X. Yu, L. Wang: **Effects of various parameters on the surface roughness of an aluminium alloy burnished with a spherical surfaced polycrystalline diamond**, International Journal of Machine Tools&Manufacture 39 (1999) pp.: 459-469. **30** D.-W. Lee, S.-S. Cho: **Comparison of X-ray residual stress measurements for rolled steels**, (2010), International Journal of Precision Engineering and Manufacturing, Vol. 12, No. 6, DOI:10.1007/s12541-011-0133-5, pp.: 1001-1008. **31** V. Mertinger, J. Sólyom, D. Cseh: **Examination of residual stress by X-Ray diffraction**, Study aid, pp.: 3-39 in: [http://www.matsci.uni-miskolc.hu/new/files/jegyzetek/diffr/segedlet\\_diffr.pdf](http://www.matsci.uni-miskolc.hu/new/files/jegyzetek/diffr/segedlet_diffr.pdf) (07.21.2017). **32** M.E. Fitzpatrick, A.T. Fry, P. Holdway, F.A. Kandil, J. Shackleton, and L. Suominen: **Determination of residual stresses by X-ray diffraction** – Issue 2; Measurement good practice guide No. 52; National Physical Laboratory, Teddington, Middlesex, United Kingdom, Sept. 2005, p.: 68, ISSN 1744-3911. **33** M. Tisza: **Metallography**, Miskolci Egyetemi Kiadó (Miskolc) 1998 p.: 396, ISBN 963 661 338 9 (In Hungarian). **34** I. Dudás: **Production Engineering I.**, Műszaki Könyvkiadó, Budapest, 2004, p.: 583, ISBN 963 661 342 7(In Hungarian).

**МИНИСТЕРСТВО ОБРАЗОВАНИЯ И НАУКИ УКРАИНЫ  
НАЦИОНАЛЬНЫЙ ТЕХНИЧЕСКИЙ УНИВЕРСИТЕТ  
«ХАРЬКОВСКИЙ ПОЛИТЕХНИЧЕСКИЙ ИНСТИТУТ»**

**Ministry of Education & Science of Ukraine  
National Technical University  
«Kharkiv Polytechnic Institute»**

**РЕЗАНИЕ  
И  
ИНСТРУМЕНТЫ  
В ТЕХНОЛОГИЧЕСКИХ СИСТЕМАХ**

---

**CUTTING & TOOLS  
IN TECHNOLOGICAL SYSTEMS**

**Международный научно-технический сборник  
International Scientific-Technical Collection**

**Основан в 1966 г. М. Ф. Семко  
Found by M. F. Semko in 1966**

**ВЫПУСК 87  
Edition № 87**

**Харьков НТУ «ХПИ» – 2017 – Kharkiv NTU «KhPI»**

ББК 34.63  
УДК 621.91

Державне видання

Свідоцтво Державного комітету телебачення і радіомовлення України

КВ № 7840 від 8 вересня 2003 року

Друкується за рішенням Вченої Ради НТУ "ХПІ"

Редакционная коллегия:

*А. И. Грабченко, д.т.н. (отв. ред.), М. Д. Узунян, д.т.н. (зам. отв. ред.),  
Агу Коллинз Агу, PhD, Н. В. Верезуб, д.т.н., Ю. Н. Внуков, д.т.н.,  
В. Л. Доброскок, д.т.н., М. Кавалец, проф., Я. Кундрак, д.т.н.,  
П. П. Мельничук, д.т.н., В. К. Старков, д.т.н., Р. С. Турманидзе, д.т.н.,  
В. А. Фадеев, проф., В. А. Федорович, д.т.н., М. Хорват, д.т.н.,  
Шаилendra Кумар Джсха, PhD, Ф. Я. Якубов, д.т.н.,  
Н. В. Крюкова (отв. секр.)*

В сборнике представлены научные статьи, в которых затрагиваются актуальные вопросы в области механической обработки различных современных материалов с применением высокопроизводительных технологий, новых методик, измерительных приборов для контроля качества обработанных поверхностей и высокоэффективных режущих инструментов. Затронуты аспекты оптимизации и математического моделирования на различных этапах технологического процесса.

Для инженеров и научных сотрудников, работающих в области резания материалов, проектирования режущих инструментов в технологических системах.

В апреле 2013 г. научный сборник «Резание и инструмент в технологических системах» включен в справочник периодических изданий базы данных Ulrisch's Periodicals Directory (New Jersey, USA)

Резание и инструмент в технологических системах: Междунар. науч.-техн. сб. – Харьков: НТУ «ХПИ», 2017. – Вып. 87. – 186 с.

**Адрес редакционной коллегии:** 61002, Харьков, ул. Кирпичова, 2, Национальный технический университет «Харьковский политехнический институт», кафедра «Интегрированные технологии машиностроения» им. М.Ф. Семко, тел. +38 (057) 706-41-43.

**ББК 34.63**

Материалы воспроизведены с авторских оригиналов

© НТУ «ХПИ», 2017